



1. PRODUCT NAME

GreyHound™

2. MANUFACTURER

GMX, Inc.
3800 E. 91st Street
Cleveland, OH 44105
Phone: 866-228-7743
Fax: 216-430-3500

3. PRODUCT DESCRIPTION

GreyHound is a commercial grade water based all-polymer spray applied waterproofing emulsion. GreyHound is solvent free; therefore it is fully compliant with VOC regulations in all 50 states. It provides seamless waterproofing protection for the most difficult jobs with tremendous elongation, strength and adhesion.

3. PRODUCT ADVANTAGES

- Commercial grade
- Will not delaminate from wall
- Solvent-free
- 100% rubber polymer emulsion

4. USES

Designed for use on parged / unparged masonry and concrete substrates. Do not backfill for 24 hours.

5. PREPARATION

All surfaces should be free from loose materials such as sand, dirt or other impediments and dry. Any cracks, spall, seems or joints should be flashed/caulked or patched. Only use when surface and air temperature is 35°F or greater during the application and for 12 hours after. Do Not apply if rain will fall with-in 12 hours after application.

6. APPLICATION

GreyHound can be applied in multiple layers or as one coating. A 38 mil thick dry coating (70 mil wet) is recommended. GreyHound should be used at a coverage rate of 22-24 sq.ft./gallon. Apply using a roller, brush or spray device. GreyHound does not have long-term stability to ultraviolet light, do not leave exposed to light more than 30 days. Gray Guard can be applied by brush, spray, or roller, and the application rate varies according to the porosity of the surface. Apply two coats for best results. **DO NOT APPLY GRAY GUARD IF RAIN IS ANTICIPATED WITHIN 6 - 8 HOURS AFTER APPLICATION.**

7. TECHNICAL SERVICES

Your local GMX representative is available to assist you in selecting the appropriate product and to provide on-site application assistance. For further information, please contact our Technical Service Dept. at 866-228-7743.

TECHNICAL DATA - GreyHound		
Property	Test Method	Value
Color		Grey
Solids		54%-56%
Elongation	ASTM D-412	2394%
Tensile Strength	ASTM D-412	575 psi
Adhesion to Concrete	ASTM C-836	Exceeds
Crack Bridging	ASTM C-836	Exceeds
Low Temp Flexibility	ASTM C-836	No Cracking
Hydrostatic Head	ASTM C-1306	40 psi
Water Vapor Permeance	ASTM E-96 Wet	0.9 perms
UV Stability		None

FLUID APPLIED
Dampproofing Paint



GMX, Inc.
3800 E. 91st Street
Cleveland, OH 44105
Toll Free: 866-228-7743
Fax: 216-430-3500
www.gmxwaterproofing.com